



# The Hazotte Quarry

CONDROZ SANDSTONE







Rubble stone (scale 1:1)



## Condroz sandstone

### ALSO KNOWN AS

Hard sandstone, Condroz psammite, Meuse sandstone, Famennian sandstone

### TYPE

Clayey sandstone, slightly micaceous and finely grained

### STRATIGRAPHICAL AGE

Upper Famennian  
(Upper Devonian, Palaeozoic)

### LOCAL QUARRY FOR A QUALITY SERVICE

Quarrying operations at the Carrière de la Hazotte go back to the beginning of the 20<sup>th</sup> century. Our family took over the ownership of the site in 1969 and our efforts over the years have turned this local quarry into an enterprise acknowledged not only in Belgium but also beyond its borders.

We developed in various sectors in order to keep abreast of market progress. Our Condroz sandstone deposit is still operational and we also specialise in the sale and purchase of old natural stone materials recovered from roadworks.

In spite of the automation of some production stations, the management wishes to keep the craft spirit alive that underpins our values and commitments. Our skilled workforce, lovers of stone, implements your projects, whether they are "routine" or tailored to your personal requirements. Customer satisfaction is their top priority. We can deliver a fast and efficient response when urgent needs arise, in different areas such as cobblestones, flagstones, kerbstones, rubble stone, stairway steps, etc. We can either draw on our stock or rely on our network of trusted partners.

Stone is a noble material wherever it is applied and whatever the shape or colour. Let our natural stone add a touch of grandeur to your home and invade your living space. Nothing has quite the charm and character of real stone.



## WORKING SITE

Carrière de la Hazotte - 4163 TAVIER

## TECHNICAL CHARACTERISTICS

### MINERALOGICAL COMPOSITION

Quartz 62-78%, lesser amounts of mica and feldspar

### ATTRIBUTES / PERFORMANCE

These data are available on [www.pierresetmarbres.be](http://www.pierresetmarbres.be) and on the sites of the official bodies, they are measured according to the procedures of European standards in force and regularly updated.

## MAXIMUM DIMENSIONS OF BLOCKS\*

Length  
2 m

Width  
1-2 m

Thickness  
0.7-1.5 m

## MINIMUM THICKNESS FOR APPLICATION\*

Horizontal elements  
2 cm



Squared rubble stone



Step



Corner

## APPEARANCE, COLOUR AND PATINA

The thick layers of sandstone display an extremely varied range of colours, with brighter shades (yellow, green, rust-brown) or more muted tones (ranging from grey-green, to grey-blue, ochre and beige). The stone takes on a rust-brown patina when it is rich in iron, whilst if rich in feldspar grey-blue or greenish tones are produced.

## FINISHED PRODUCTS AND STANDARD DIMENSIONS

Thanks to its outstanding mechanical qualities, sandstone lends itself admirably to applications using every type of rubble stones, steps, wall coverings, quoins, surrounds for bay windows, dressed faces, for exterior use as well as for interior and decorative purposes. Its natural anti-skid qualities make it ideal for floor-covering; setts, thin paving tiles, edgings.

### Rubble stones

height 3-7 / 5-10 / 8-16 / 10-20 cm, minimum length 1.5 x the height  
depth 8-12 / 10-15 / 10-20 / 15-20 / 15-25 cm

### Floor tiles

in free form 30-40 cm, thickness 2-4 / 4-7 cm  
rectangular format, free measurement 15-30 x 25-30 cm  
free length, width 15/20/25/30 cm, thickness 4-7 / 2-8 cm

### Mosaic paving

5-7 / 7-9 / 8-10 / 9-11 / 10-12 cm

### Setts

width 12-14 / 14-16 / 15-17 cm, thickness 5-8 / 8-10 / 10-12 / 5-15 cm

Non-standard dimensions and advice on application and maintenance, can be obtained directly from the producer..

## SURFACE TREATMENTS AVAILABLE

Cleaved and retouched to a grater or lesser degree, to even out the contours of the pieces for all forms of rough, retouched and squared finish.

## DESCRIPTIVE SPECIFICATIONS

«Clayey sandstone, slightly micaceous, very finely grained, stratigraphical age Upper-Famennian (Upper Devonian, Palaeozoic)».




[\*] Values shown are for reference only.



## CARRIÈRE DE LA HAZOTTE

Grand-Route, 7 · B-4163 TAVIER  
 Tel. +32 (0)4 383 64 56 · Fax. +32 (0)4 383 64 71  
 info@hazotte.be · www.hazotte.be  
 VAT BE 0406 897 083 · RPM Huy  
 Manager : Harrie Verhoeven



Arch. Hublaor



Semi-dressed rubble stone



Arch. Pissart



Dry-stones walls



Roughly dressed rubble stone masonry



PIERRES & MARBRES WALLONIE

